

# PAPEL KRAFT 2ª LISO

## FICHA TÉCNICA: KTECH 2 60-70-80 GRS

<b>Grammatura</b> <i>Substance - Flächengewicht - Grammage</i>	gr/mq	<i>Metodo prova ISO</i>	<b>60</b>	<b>70</b>	<b>80</b>
<b>Carico di rottura M.D.</b> <i>Tensile Strength - Laufriichtung Bruchlast - Charge de rupture</i>	KN/m	1924/3	4,12	4,81	5,41
<b>Carico di rottura C.D.</b> <i>Tensile Strength - Laufriichtung Bruchlast - Charge de rupture</i>	KN/m	1924/3	1,65	1,92	2,19
<b>Allungamento M.D.</b> <i>Elongation - Laufriichtung Streckung - Allongment</i>	%	1924/3	1,7	1,7	1,7
<b>Allungamento C.D.</b> <i>Elongation - Laufriichtung Streckung - Allongment</i>	%	1924/3	4	4	3,7
<b>Lunghezza di rottura M.D.</b> <i>Breaking length - Laufriichtung reilnge - Longueur de rupture</i>	m	1924/3	7000	7000	6900
<b>Lunghezza di rottura C.D.</b> <i>Breaking length - Laufriichtung reilnge - Longueur de rupture</i>	m	1924/3	2800	2800	2800
<b>Media</b> <i>Length - Querrichtung - Moyenne</i>	m	-	4900	4900	4850
<b>Indice lacerazione M.D.</b> <i>Tear index - Durchreifung - Indice de dchirement</i>	mNmq/g	1974	6	6,5	6,5
<b>Indice lacerazione C.D.</b> <i>Tear index - Durchreifung - Indice de dchirement</i>	mNmq/g	1974	7,5	8	8
<b>Porosit Gurley MF</b> <i>Porosit gurley - Porosit Gurley - Porosit Gurley</i>	sec	5636/5	30 < x < 40	30 < x < 40	30 < x < 40
<b>Porosit Gurley C</b> <i>Porosit gurley - Porosit Gurley - Porosit Gurley</i>	sec	5636/5	40 < x < 50	40 < x < 50	40 < x < 50
<b>Cobb 60"</b>	gr/mq	535	26	28	29
<b>Resistenza allo scoppio</b> <i>Bursting Strength - bersten - Resistance d'eclatement</i>	KPa	2758	165	200	210
<b>Bendsten Test Top</b> <i>Con calandra - With Calander</i>	ml/min	8791-2	360 < x < 420	360 < x < 420	360 < x < 420
<b>Bendsten Test Bottom</b> <i>Con calandra - With Calander</i>	ml/min	8791-2	670 < x < 730	670 < x < 730	670 < x < 730
<b>Resistenza Residua (se richiesto)</b> <i>Treatment Wet Strength (if requested)</i>	%	1924/3	20 < x < 25	20 < x < 25	20 < x < 25

*I valori riportati in tabella sono garantiti con un intervallo del +/- 5%*  
*The values, reported on the table, are guaranteed in a range of +/- 5%*  
*Die angegebenen Werte unterliegen einer Toleranz von +/- 5 %*



100% Carta Riciclata